



Earth fiber™



EARTH FIBER 60/30 GLUED HOOKED END STEEL FIBER PRODUCT DATA SHEET



EARTH FIBER™ 60/30 Glued Hooked End Steel Fibers are designed specifically for the reinforcement of concrete, mortars and other cementitious mixes. EARTH FIBER™ 60/30 is a cold drawn wire fiber, Glued Hooked End to provide optimum performance within the concrete mix. EARTH FIBER™ 60/30 Glued Hooked End steel fibers are ASTM compliant and specifically designed to meet or exceed the defined performance requirements.

Why Earth Fibrex :

- 1. Best Quality at Competitive Prices:** Our steel fibers are known for their superior quality, providing reliable and long-lasting reinforcement, all at competitive prices.
- 2. Extensive Product Range:** We offer a wide range of steel fiber options to cater to different concrete strengthening needs, ensuring the perfect solution for your project.
- 3. Large Manufacturing Capacity:** Our robust manufacturing capacity allows us to efficiently meet the demands of projects of all sizes, ensuring timely delivery.
- 4. Commitment to Integrity and Trust:** We prioritize maintaining strong relationships with our customers by operating with integrity and building trust.
- 5. ISO and CE Certification:** Our steel fibers are ISO and CE certified, guaranteeing their compliance with international standards of quality and safety.

Primary Applications:

- Ground Supported Slabs
- Jointless Floors
- External Roads & Pavements
- Manhole Covers
- Residential Application
- Tunnel Application

Compliance:

- Conforms to ASTM A820, Type I cold drawn wire
- Testing conforms with ASTM A820
- Testing conforms with BS EN 14889-1

Type:

Glued Hooked End

Features & Benefits:

- Provides uniform multi-directional concrete reinforcement.
- Increases crack resistance, ductility, energy absorption or toughness of concrete.
- Improves impact resistance, fatigue endurance and shear strength of concrete.
- High tensile strength fibre bridging joints and cracks to provide tighter aggregate interlock resulting in increased load carrying capacity.
- Provides increased ultimate load bearing capacity which allows possible reduction of concrete section.
- Requires less labour to incorporate into concrete than conventional reinforcement.
- Offers economical concrete reinforcement solutions with greater project scheduling accuracy.
- Ideally suited for hand or vibratory screeds, laser screeds and all conventional finishing equipment.

Nominal Dimensions:

- Diameter D : 0.60 mm;
- Length L : 30 mm;
- Aspect Ratio L/D: 50
- No. of Fibres per kg: 14221

Mechanical Properties:

- R_m (Tensile strength of the wire): > 1250mPa .
- A_l (Strain at failure): <4%
- Camber of the Fiber: max. 5% of L'
- Young's Modulus: 2,00,000 N/mm2 Approx.

PRODUCT USE

Mixing designs and procedures:

Earth fiber™ 60/30 Hooked End steel fibers can be added during or after the batching of the concrete but should never be added as the first component. Such devices as conveyor belts, chutes and dispensers may be used to add fibers to the mixer at the ready mix plant. After the fibers have been added, the concrete should be mixed for sufficient time (minimum 5 minutes at full mixing speed) to ensure uniform distribution of the fibers throughout the concrete. The use of mid or high-range water reducing admixtures can be advantageous, but is not essential.

Placing:

Earth fiber™ 60/30 Hooked End steel fibers can be pumped and placed using conventional equipment. Hand or vibratory screeds and laser screeds can be used with Earth fiber™ 60/30 Hooked End steel fibers.

Finishing:

Conventional finishing techniques and equipment can be used when finishing Earth fiber™ 60/30 Hooked End steel fibers concrete. In some cases an extra bull float process is advised and lowering the angle of the power float blades will help to minimize fibre exposure on the surface.

Dosage rate:

The fiber dosage will vary depending on the type of application, concrete mix design and the performance / toughness requirements of each particular project. Typically, steel fiber dosage will be in the range of 10 kg to 40 kg per cubic meter. Earth Fibrex Infra Pvt. Ltd. technical team can offer advice on dosage requirements once performance requirements have been established by the project designer / engineer.

Compatibility:

Earth fiber™ 60/30 Hooked End steel fibers are compatible with all curing compounds, super plasticizers, water reducers, hardeners and coatings.

Fiber network:

- 6.863 fibers/kg
- 4.124 m/m³ at 10 kg/m

Safety:

It is recommended that gloves and eye protection be used when handling or adding Earth fiber T™ 60/30 Hooked End steel fibers to concrete.

Packaging:

Earth fiber™ 60/30 Hooked End steel fibers are available, as standard in 25 kgs Bag.

Technical services:

Earth Fibrex Infra Pvt. Ltd. is backed by our team of reinforced concrete consultants who can carefully analyze each project and provide fiber reinforced concrete design solutions to ensure maximum project performance and cost efficiency.

References:

- ASTM A820 Standard Specification for Steel Fibers for Fibre Reinforced Concrete.
- BS EN 14889-1.
- ASTM C1116 Standard Specification for Fiber- Reinforced Concrete and Shotcrete.
- ASTM C1018 Standard Test Method for Flexural Toughness and First Crack Strength of Fiber-Reinforced Concrete.
- IRC:SP:46:1997 Code of Indian Road Congress.
- IS:12592:2002 SFRC Manhole covers.

Specification clause:

Fibers for concrete shall be Earth fiber™ 60/30 Hooked End steel fibers conforming to ASTM-A-820M Type I and manufactured from cold drawn wire with a minimum tensile strength of 1250 mPa / N/mm².

MANUFACTURED BY:

EARTH FIBREX INFRA PVT. LTD.

EFIPL - Kh. 633 Killa - 141/2/2/4 Bhatgaon Dogran,
Sonipat Haryana - 131022

Contact: +91 9711151541, 9313251541

Website: www.earthfibrex.com

Mail: info@earthfibrex.com

earthfibrex.infra

GEOMETRY EARTH FIBER™ 60/30 Loose Hooked End Steel Fiber




Figure 1

D=0.60mm
L=30mm
A/R=50
Tolerance for D/L ±10%
As per ASTM & BS EN Standards



Conforms to
ASTM A-820M 06



AN ISO
9001:2015
Certified Company